

## Ficha Técnica Comercial Technical Commercial Sheet

Terrassa 01 de enero de 2023

Artículo / Article: **8015 – VOLTERRA BIO WR**



### Composición / Composition:

**1ª capa / 1st. layer: 94% Poliéster/Polyester + 6% EA/EA + Hidrorepelente BIO/Water Repellent BIO**  
**2ª capa / 2st. layer: 100% Membrana Poliester Hidrofilo / Hydrophilic Polyester membrane**  
**3ª capa / 3st. layer: 93% Poliéster / Polyester + 7% EA / EA**

- **Peso / Weight:** 223 gr/m<sup>2</sup> ± 10 %
- **Ancho / Width:** 148 cm ± 2 %
- **Metraje Piezas / Roll Length :** 50,- mts.

### Características del tejido / Fabric's Characteristics:

- **Transpirabilidad de la membrana / membrane breathability:**

ASTM E96-BW:1996                      11.400 gr/m<sup>2</sup> 24h  
RET:

- **Impermeabilidad / water column :**

Water column:                                      ≥ mm

- **Uso / Use:**

**Estampación a 190°C y 45" / Printing at 190°C , 45"**  
**(recomendamos efectuar test de sublimación, para centrar parámetros de temperatura, tiempo y calidad).** (We recomend to make sublimation test to set temperature, time and quality parameters)

- **Advertencia / Warning:**

**Recomendamos NO utilizar suavizante en el proceso de lavado, podría alterar el grado de transpirabilidad de la membrana "zero wind" del tejido./ We recommend NOT to use fabric softener during the wash step which can affect the level of breathability of the "zero wind" membrane present in the fabric.**

### Mantenimiento / Care:

